

MECHANICAL PROPERTIES

ALT/CBRSB/(PE,PV)/1

CLEAR CAST SHEET, BLOCK, ROUND ROD & SQUARE BAR



ALTERNATIVE PLASTICS

ALT CAST acrylic is a thermoplastic polymer obtained by mass polymerisation of pure monomer and is distinguished by its extreme PURITY and TRANSPARENCY together with:

- EXCELLENT MECHANICAL MACHINING
- BRILLIANCY AND VARIETY OF COLOURS
- EXCELLENT RESISTANCE TO LIGHT AND AGEING.
- EASY THERMOFORMING
- LIGHTNESS AND TOUGHNESS

SPECIFICATIONS OF ALT CAST Acrylic

The properties according to the methods used refer to tests done on clear sheets having a 3mm thickness at temperature of 23°C and 50% R.H.

PROPERTIES	ASTM METHOD			DIN METHOD		
		UNIT			UNIT	
DENSITY (SPECIFIC WEIGHT)	1.19	g/cm ²	D792	1.19	g/cm ²	53479
WATER ABSORPTION	0.25	%	D570	25	mg	53495
MODULUS OF ELASTICITY	32000	Kg/cm ²	D790	3200	N/mm ²	53455
TENSILE STRENGTH	740	Kg/cm ²	D638	74	N/mm ²	53452
FLEXURAL STRENGTH	1200	Kg/cm ²	D790	120	N/mm ²	53455
ELONGATION AT BREAK	3	%	D638	3	%	53453
IMPACT STRENGTH WITH NOTCH (IZOI)	2	Kg cm/cm ²	D256	2	KJ/m ²	53453
IMPACT STRENGTH UNNOTCHED (CHARPY)	25	Kg cm/cm ²	D256	27	Kg/m ²	53453
ROCKWELL HARDNESS	M100	-	D785	-	-	-
BALL DROP H98/30	-	-	-	200	N/mm ²	53453
COEF. OF THERMAL CONDUCTIVITY	5.104	cal/cm/s°C	C177	0.19	W/m°C	52612
DEFLECTION TEMP. (1.8N/mm ²)	105	°C	D648	105	°C	53461
SOFTENING POINT	>=115	°C	D1525	>=115	°C	53460
COEF. OF LINEAR THERMAL EXPANSION	7.5.10-5	1/°C	D696	70.10-4	1/°C	VDE0304/1
SPECIFIC HEAT	0.35	cal/g°C	-	-	-	-
REFRACTIVE INDEX n ₂₀ /D	1.49	-	D542	1.49	-	53491
LIGHT TRANSMITTANCE	92	%	D1003/A	92	%	5036
HAZE	0.5	%	D1003/A	-	-	-
DIELECTRIC STRENGTH	20	KV/mm	D149	20	KV/mm	53481
VOLUME RESISTIVITY	1015	Ohm/cm	D257	-	-	-
SURFACE RESISTIVITY	1414	Ohm	D257	1014	Ohm	53482
TRANSVERSAL RESISTIVITY	>1015	Ohm/cm	D257	>1015	Ohm/cm	53482
DIELECTRIC CONSTANT (50Hz)	3.5	-	D150	3.5	-	53483
POWER FACTOR (50Hz)	0.05	-	D150	0.06	-	53483

RESISTANCE TO CHEMICAL AGENTS ACIDS, BASES AND INORGANIC SALT. Please enquire.

The data, information and suggestion given are purely an indication, Alternative Plastics does not assume any responsibility whatsoever for results or application due to their use, or which are in opposition to existing patents.